

EP03/12164

PCT/EP03/12164

EPO - DG1

26 NOV 2003

112

PA 1088624

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

November 03, 2003

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 60/427,409

FILING DATE: November 19, 2002

REC'D 13 JAN 2004

WIPO PCT

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS



E. Bornett
E. BORNETT
Certifying Officer

11-2002

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
 PTO/SB/18 (10-01)
 OMB 0531-0032
 10/31/2002

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No.

EV 097483480 US

INVENTOR(S)

Given Name (first and middle [if any])	Family Name or Surname	Residence (City and either State or Foreign Country)
Eleco Titus Carel Johannes Petrus Jozef	Vogt Verlaan	Culemborg, Netherlands Deventer, Netherlands

☐ Additional inventors are being named on the _____ separately numbered sheets attached hereto

TITLE OF THE INVENTION (500 characters max)

FISCHER-TROPSCH CATALYST COMPOSITION

Direct all correspondence to:

CORRESPONDENCE ADDRESS

☐ Customer Number

OR

☒ Firm or
Individual Name

LOUIS A. MORRIS

Address

AKZO NOBEL INC.

Address

7 LIVINGSTONE AVENUE

City

DOBBS FERY

State

NY

ZIP

10522-3408

Country

USA

Telephone

(312) 906-7769

Fax

(914) 906-7771

ENCLOSED APPLICATION PARTS (check all that apply)

☒ Specification Number of Pages

5

☐ Drawing(s) Number of Sheets

☐ CD(s), Number

☐ Application Data Sheet. See 37 CFR 1.76

☐ Other (specify)

METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT

☐ Applicant claims small entity status. See 37 CFR 1.27.

☐ A check or money order is enclosed to cover the filing fees

☒ The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number:

01-1350

☐ Payment by credit card. Form PTO-2038 is attached.

FILING FEE
AMOUNT (\$)

\$160.00

The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.

☒ No.

☐ Yes, the name of the U.S. Government agency and the Government contract number are:

Respectfully submitted,

SIGNATURE

Date

11/19/02

TYPED or PRINTED NAME Lainie E. Parker

REGISTRATION NO.

36,123

TELEPHONE (914) 674-5466

(if appropriate)

Docket Number:

ACH2969 PRUS

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

ACH 2969 PRUS

FISCHER-TROPSCH CATALYST COMPOSITION

The present invention relates to a catalyst composition suitable for the conversion of carbon monoxide and hydrogen to C_5^+ hydrocarbon mixtures, comprising a Fischer-Tropsch catalyst component and an acidic component.

5 The invention further relates to a process for the conversion of carbon monoxide and hydrogen to C_5^+ hydrocarbon mixtures using this catalyst.

10 It is known to convert carbon monoxide and hydrogen to larger hydrocarbons using a composition comprising a Fischer-Tropsch catalyst component and an acidic component.

For instance, US 4,595,702 discloses a Fischer-Tropsch process using an copper-containing iron catalyst as Fischer-Tropsch catalyst component and a zeolite selected from the group of ZSM-5, ZSM-45 and zeolite beta as the acidic component.

15

US 4,556,645 discloses the combined use of a Fischer-Tropsch catalyst component and a crystalline, microporous silicoaluminophosphate, non-zeolitic molecular sieve as the acidic component.

20 It has now been found that a better performance can be reached when zeolite Y is used as the solid acid. This zeolite Y may be steam-stabilized or non-steam-stabilized. More preferably, zeolite Y contains a metal compound, e.g. a transition metal and/or rare earth metal compound.

Hence, the present invention relates to a catalyst composition suitable for the conversion of carbon monoxide and hydrogen to C_5^+ hydrocarbon mixtures, comprising

25

- (a) a Fischer-Tropsch catalyst component, and
- (b) zeolite Y.

30 This zeolite Y preferably has a SAR of above 4.0, more preferably 5.0-10.0 and preferably contains one or more metal compounds. Examples of suitable metals

are rare earth metals, e.g. Ce, La, and transition metals of Groups IV-VIII of the Periodic System, e.g. V, Cr, Mn, Fe, Co, Ni, Cu, Zr, Nb, Ru, Re, etc.

The metal compound is preferably present in or on the zeolite in amounts of 0.1 to 10 wt%, more preferably 0.3 to 2 wt%, calculated as oxide.

- 5 The metal compound can be supported on the zeolite Y in any manner known in the art. Examples of such methods are impregnation, ion-exchange, and deposition precipitation of soluble metal salts.

If desired, the metal-containing zeolite Y is calcined after the metal compound has been deposited.

10

The Fischer-Tropsch catalyst component can be any conventional Fischer-Tropsch catalyst, preferably comprising iron and/or cobalt. For the preparation of such catalysts it is referred to, e.g., WO 01/97968, WO 01/89686/ and WO 01/70394.

- 15 The Fischer-Tropsch catalyst component can be promoted with various metals, e.g. Al, Ti, Cr, Mn, Ca, Na and/or K. Furthermore, the Fischer-Tropsch catalyst component can contain binder materials, such as silica and/or alumina.

20 The amount of zeolite Y in the catalyst composition according to the invention preferably ranges from 5 to 40 wt%, more preferably from 10 to 30 wt%, based on the total weight of the catalyst composition.

The catalyst composition can be a physical mixture of Fischer-Tropsch catalyst component particles and zeolite Y particles. On the other hand, the catalyst composition can also comprise one type of particle, containing both the Fischer-Tropsch catalyst component and the zeolite Y.

25 The invention further relates to a process for the conversion of carbon monoxide and hydrogen to C_5^+ hydrocarbon mixtures, said process comprising contacting carbon monoxide and hydrogen with the above catalyst composition
30 comprising a Fischer-Tropsch catalyst component and zeolite Y.

This process can be carried out in any suitable reactor, such as a (fixed) fluidised bed reactor.

This process is preferably a high-temperature Fischer-Tropsch process. The temperature ranges preferably from 250° to 400°C, more preferably from 300° to 370°C, and most preferably from 330° to 350°C. The pressure preferably ranges from 10 to 60 bar, more preferably 15 to 30 bar, and most preferably about 20 bar.

The H₂/CO volume ratio preferably ranges from 0.2 to 6.0, preferably 0.5-6, most preferably 1-3.

10

The resulting hydrocarbon product preferably contains, on a mass basis, at least 35%, more preferably at least 45%, and most preferably at least 50% of C₅⁺ compounds. The process may be used for the production of aromatics, branched hydrocarbons, and/or olefins. Preferably, the process is used for the production of liquid fuel, especially gasoline and preferably unleaded gasoline.

15

CLAIMS

1. Catalyst composition suitable for the conversion of carbon monoxide and hydrogen to C_5^+ hydrocarbon mixtures, comprising
 - 5 (a) a Fischer-Tropsch catalyst component, and
 - (b) zeolite Y.
2. Catalyst composition according to claim 1 wherein the zeolite Y contains a metal compound.
- 10 3. Catalyst composition according to claim 2 wherein the metal compound comprises a metal selected from the group consisting of Group IV metals, Group V metals, Group VI metals, Group VII metals, Group VIII transition metals, rare earth metals, and combinations thereof.
- 15 4. Catalyst composition according to any one of claims 1-3 wherein the Fischer-Tropsch catalyst component comprises iron.
- 20 5. Catalyst composition according to any one of claims 1-3 wherein the Fischer-Tropsch catalyst component comprises cobalt.
- 25 6. Catalyst composition according to any one of the preceding claims wherein zeolite Y is present in the catalyst composition in an amount of 5 to 40 wt% based on the total weight of the catalyst composition.
7. Process for the conversion of carbon monoxide and hydrogen to C_5^+ hydrocarbon mixtures, said process comprising contacting carbon monoxide and hydrogen with a catalyst composition according to any of the claims 1-6.

Abstract

The present invention relates to a catalyst composition suitable for the conversion of carbon monoxide and hydrogen to C_5^+ hydrocarbon mixtures. This catalyst composition comprises a Fischer-Tropsch catalyst component and zeolite Y. Preferably, the zeolite contains one or more metal compounds.